TECHNICAL DATA

KAPTON® POLYIMIDE FILM TAPE

Product Code: 1K063CR (Flame Retardant)

P. LEO & CO LTD

P.O. Box 175 Fo Tan, Shatin, Hong Kong.
Telephone: (852) 2604-8222 * Facsimile: (852) 2693-2093
E-mail: sales@pleo.com * Web Site: http://www.pleo.com



91 UL FILE #E126174

1.0

Description: 1K063CR is made by Kapton ® CR polyimide 1mil film tape with Silicone adhesive.

Highly heat resistance up to temperature 220°C and Flame retardant. The Corona resistance of Kapton ® CR to compare with the standard Kapton ® HN at a voltage stress of 20KV/mm (500 V/mil)AC at 50Hz, for example Kapton ® CR has a life endurance in excess 100,000 hr (11 ½ years), in comparing to 200 hours for Kapton ® HN. Similar substantial improvements in corona resistance and outstanding high temperature retention of physical and electrical properties found with Kapton ® CR.

This product complies with the flame Retardant requirements of UL 510.

Application: For use in high performance electrical applications, used on high-temperature or high

voltage coils, such as in traction machine manufacturing, in the production of generators,

capacitors transformers etc.

Technical Details : <u>PROPERTIES</u> <u>UNITS</u> <u>SPECIFICATION</u>

COLOR amber TOTAL THICKNESS 0.063 ± 0.006 mm TENSILE STRENGTH kg/25mm 11 **ELONGATION** 55 ADHESION TO STEEL kg/25mm 0.6 UNWIND FORCE kg/25mm 1.0 kV DIELECTRIC BREAKDOWN $1x10^{12}$ INSULATION RESISTANCE ohm TEMPERATURE RATED ^{0}C 220

Test Method: In accordance with ASTM method

Shelf Life: 6 months when storage at 23°C and 65% relative humidity

Availability: Standard 33M roll 3" core, width 620mm

CORROSION FACTOR

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness there of is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be device. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or *he inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection there with.



^{*}KAPTON is a registered trademark of DuPont