TECHNICAL DATA

POLYIMIDE FILM TAPE Product Code: 1K12A (Flame Retardant)

P. LEO & CO LTD

P.O. Box 175 Fo Tan, Shatin, Hong Kong. Telephone : (852) 2604-8222 * Facsimile : (852) 2693-2093 E-mail : sales@pleo.com * Web Site : http://www.pleo.com





SUL FILE #E126174

- Description : 1K12A is a 0.0125mm thick Polyimide film coated with <u>Acrylic based</u> thermosetting pressure sensitive adhesive. Outstanding, high temperature retention of physical and electrical properties. This product complies with the <u>flame Retardant</u> requirements of UL 510.
- Application :For use in high performance electrical applications, used on high-temperature coils, such
as in traction machine manufacturing, in the production of generators, capacitors
transformers etc. May also be used for masking off gold contacts on PC boards during
wave soldering process and during hot air level. It is used as insulation material of Class
R

			OPE CIEVE ATION
Technical Details :	<u>PROPERTIES</u>	<u>UNIT</u>	SPECIFICATION
	COLOR	-	amber
	TOTAL THICKNESS	mm	0.03 ± 0.003
	BACKING THICKNESS	mm	0.0125
	TENSILE STRENGTH	kg/25mm	5
	ELONGATION	%	60
	ADHESIVE TO STEEL	kg/25mm	0.3
	DIELECTRIC BREAKDOWN	kV	3.5
	UNWIND FORCE	kg/25mm	0.8
	INSULATION RESISTANCE	ohm	1×10^{12}
	TEMPERATURE CLASS	°C	180
	CORROSION FACTOR	-	1.0
Test Method :	In accordance with <u>ASTM</u> method		

Shelf Life : 6 months when storage at 23°C and 65% relative humidity

Availability : Standard 33M roll, 3" core, width 500mm

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness there of is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer's shall be liable for any injury loss or damage direct or consequential arising out of the use of or *he inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection there with.



